



## MCON MAGIC COAT DP

HIGH PERFORMANCE DAMP  
PROOF COATING



### Product Description :-

MCON MAGIC COAT DP is a fibre reinforced elastomeric liquid applied waterproofing membrane. It is formulated with select elastomeric and resilient acrylic polymers and reinforcing polyester fibres. Upon curing, it forms a thick, seamless, durable membrane thus offering ultimate waterproofing. MCON MAGIC COAT DP is elastomeric in nature and has good resistance to weather and sunlight.

### Features & Benefits :-

- Elastomeric – On that accommodate cracks up to 2 mm with an elasticity of 100-150%.
- Low water permeability – excellent resistance to ingress of water.
- Adhesion – excellent adhesion to concrete and masonry surfaces.
- Elongation at Break - The elongation of the unreinforced system after 7 days cure at 68°F (20°C) when tested against BS 2782 or similar test method is typically 90%.

### Areas of Application :-



*Terrace Garden*



*Podiums*



*Dead Walls*



*External Walls*

### Technical Details :-

Appearance	Thixotropic liquid
Color	White
Waterproofing	Up to 7 bars hydrostatic pressure
Viscosity	1.6 - 3.5 poise at 25°C
Density	1.35 - 1.40 g/cm <sup>3</sup>
Solids	50 - 55 %
Solvent	Water
Flash Point	None
Specific Gravity	1.40 - 1.45





## MCON MAGIC COAT DP

HIGH PERFORMANCE DAMP  
PROOF COATING



### Easy To Apply :-

- All surfaces to be waterproofed should be sound, clean and dry and free of any laitance, grease and oil, dirt and other loose materials.
- Algae and fungi must be removed physically. After treatment leave for 2 - 3 hrs and then wash down thoroughly with clean water and allow to dry completely.
- MCON MAGIC COAT DP should be applied by brush, trowel, airless spray in two coats maintaining the spreading rate to achieve the desired DFT of 1 mm. The material consumption shall be approximately 0.2 to 0.3 kg / m<sup>2</sup> per 2 coats.
- In critical applications where film thickness is paramount and desired than the stated one then two coats should be applied with quantities per coat gauged to give the specified final film thickness.
- On a vertical surface if high film build up is desirable then additional coat may be required.
- If the coated surface is to be further subject to abrasion then sprinkle sand on the surface when the coating is in wet condition. This will ensure protection of the membrane.
- The coating will get fully cured into membrane in 7 days. If a water ponding test is to be run, the membrane should be fully cured.



### Coverage :-

25 - 35 Sq. ft. / kg  
in 2 coats



### Packing :-

20 Kgs

### Shelf Life :-

- 12 months in original packing if stored at room temperature i.e.25° C

### Precautions & Safety :-

- Surface to be dry for application as the material is not cured in presence of moisture.
- Moisture level shall not be essentially more than 0.5%.
- Soft settling is likely to be observed in containers and the same shall be stirred thoroughly and carefully to achieve a homogeneous consistency.
- Avoid application on very hot substrate & during a very hot and windy conditions.
- Film formation may not be uniform and gradual under such circumstances & skinning on top surface may lead to formation of blisters and bubbles due to entrapped vapour from within the material.

An ISO 9001 : 201 - An ISO 14001 : 2015 - AN BS OHSAS 45001 : 2018

**MCON RASAYAN PVT. LTD.**

Trusted Partner In Construction Chemicals

Corporate Office : Gala No. 6 , Bardanwala Estate , Bandivali Hill Road , Jogeshwari (W) , Mumbai - 400 102 , Maharashtra , India .

Consumer Care : 022 - 26790031 • Email Id : [info@mconrasayan.com](mailto:info@mconrasayan.com) • Visit us : [www.mconrasayan.com](http://www.mconrasayan.com) • Follow Us :   