



MCON NSA WHITE (GOLD)

READY TO USE POLYMERISED WHITE TILE ADHESIVE FOR LARGE FORMAT MARBLES & GRANITE



Product Description :-

White, high polymer modified, cement-based wall and floor marble adhesive. NSA WHITE (GOLD) is suitable for fixing large format marble, granite and natural stones in interior and exterior situations, including swimming pools. MCON NSA WHITE is ideal for concrete, plaster and also tile substrates.

Features & Benefits :-

- High Bond strength with no shrinkage - hence can be used for large format fixing applications apart from fixing marble on concrete and plaster substrates.
- White coloured adhesive ensures true reflection of marble to give real Marble effect which is not the case with Grey adhesives.
- Prepacked factory controlled ensures consistent quality.
- Spreads quickly and easily. Excellent waterproofing characteristics.

Areas of Application :-



Large Format Tile



Terrazzo & Natural Stone



Marble



Large Format Composite Stone

MCON NSA WHITE GOLD CERTIFIED BY :-



Fields Of Use :-

- Fixing poorly absorbent or non-absorbent materials such as: single fired tiles, split tiles and refined porcelain stoneware, outdoor use, indoor use on walls and floors ; for fixing absorbent tiles made of : cotto, twice-fired, single-fired ceramic.
- Suitable for use when high performances are required, such as : tile fixing in industrial environments, or fixing on top of old ceramic tiles, in swimming pools or on facades.
- Spot-gluing insulating panels made of polystyrene, polyurethane foam, rock or glass wool.
- Fixing natural stone and marble, so long as they are not affected by water.
- For tiles & stones having weight of <math>< 60 \text{ kg} / \text{m}^2</math>. Fixing on heating floors.



TILE ADHESIVE & GROUT



MCON NSA WHITE (GOLD)

READY TO USE POLYMERISED WHITE TILE ADHESIVE FOR LARGE FORMAT MARBLES & GRANITE



Amount Required :-

Trowel	8 x 8 mm	10 x 10 mm	15 mm
MCON NSA WHITE (GOLD)	3 Kg / m ²	4 Kg / m ²	5 Kg / m ²



Technical Specification :-

Bed Thickness	4 - 6 mm		
Open Time	30 Minutes		
Pot Life	3 hours		
Final Setting Time	24 hours	Initial Setting Time	20 Min
Temperature Resistance	-5° C to 80° C		
Dry Density	1.50 - 1.55 g/cc		
Wet Density	1.75 - 1.80 g/cc		
Can be subjected to traffic	*After 4-6 hrs		
Floor tiles can be grouted	*After 24 hrs		
Wall tiles can be grouted	*After 4 hrs		
Surface can be used	*After 48 h (72 h tanks and swimming pools)		
Creep on a vertical wall	0 mm °	Reqd. ≤ 0,5 mm EN 1308	
Bond after 24 h	0.8 N/mm ²	Reqd. > 0,5 N/mm ² EN 1348	
Pull Out Bond Strength	1.1 Mpa	@14 days	
Compressive strength	12 N/mm ²	EN 196	
Curing Time	10 Minutes		

- According to standard EN 12004

- These times refer to a temperature of 23°C — 50% RH. They become shorter with higher temperatures and longer at lower temp.

Standards :-

- MCON NSA WHITE (GOLD) meets the performance requirements of BS.5980:1980 (The United Kingdom) and is a CE Certified Product. It is a ISI Certified Product as per IS 15477.

TILE ADHESIVE & GROUT



MCON NSA WHITE (GOLD)

READY TO USE POLYMERISED WHITE TILE ADHESIVE FOR LARGE FORMAT MARBLES & GRANITE



Easy To Apply :-

- Spread MCON NSA WHITE (GOLD) on the surface not more than 2 sq.m. at a time, apply the adhesive to the wall or floor surface.
- Comb the adhesive to the required depth (between 3 - 6 mm) using a suitable trowel.
- Press the marble firmly into position with a slight twisting action, checking periodically that good contact is maintained with the back of each tile.
- Leave no voids behind tiles when solid-bed fixing.
- Tiles should be fixed within 20 minutes of adhesive being applied, depending on the porosity of the surface and atmospheric conditions.
- Tiles can be adjusted up to 10 - 15 minutes after fixing. Touch the adhesive ribs periodically and if a skin has formed, remove the adhesive and apply a new layer.
- Leave adequate joints between individual wall and floor tiles unless self spacing tiles are used.
- Clean off surplus adhesive from the tile face and between joints.
- Do not use in damp conditions and temperature less than 5° C.



Coverage :-

20 kg of MCON NSA WHITE (GOLD) will cover 3 to 3.5 m² with recommended thickness of 4 to 5 mm



Packing :-

20 & 50 Kgs

Shelf Life :-

- MCON NSA WHITE (GOLD) will have a shelf life of 12 months in unopened containers when kept in dry conditions at a temperature between 5°C to 45°C.

Safety & Precautions :-

- MCON NSA WHITE (GOLD) is non-toxic. However, splashes on the skin should be washed well with water and in contact with eye occurs, wash well with water and seek medical advice.

An ISO 9001 : 2015 - An ISO 14001 : 2015 - AN BS OHSAS 45001 : 2018

MCON RASAYAN PVT. LTD.

Trusted Partner In Construction Chemicals

Corporate Office : Gala No. 6 , Bardanwala Estate , Bandivali Hill Road , Jogeshwari (W) , Mumbai - 400 102 , Maharashtra , India .

Consumer Care : 022 - 26790031 • Email Id : info@mconrasayan.com • Visit us : www.mconrasayan.com • Follow Us :   